

4500 Roof



Dry Adhesion (lbf)	Black	White
Aluminum	14.51/100c	11.71/100c
Brick	15.51/90c	10.34/90c
Concrete	13.41/100c	12.56/100c
EPDM (Black or White)	8.87/100c	5.16/20c
Galvanized Steel	13.79/100c	10.56/100c
Glass	13.78/100c	11.31/100c
Luan (Wood)	10.99/65c	11.80/100c
Shingle	6.39/100a sf	6.37/sf
Steel	13.48/100c	11.54/100c
Tile	14.29/100c	11.30/100c
Vinyl	13.15/95c	11.11/100c
Tensile at Peak (psi)	248.3	106.99
Elongation at Break (%)	324	428.33
Type "A" Hardness	35	29
Tack Free time (ASTM method)	90 min	40 mins
Cure rate by weight loss	1 day	4 days

Geocel
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

6/2011